

产品型号	H8202-I	产品名称	PA6改性
测试项目 Test Properties	测试方法 Test method (ASTM)	单位 Unit	数据
拉伸强度 Tensile Strength	D638	Mpa	69
断裂伸长率 Elongation at break	D638	%	23.6
弯曲强度 Flexural Strength	D790	MPa	94
弯曲模量 Flexural Modulus	D790	MPa	2288
缺口冲击强度 Impact Strength 23℃	D256	J/m	60
玻纤含量 Glass Fiber content	D1506	%	0
密度 Density	D792	g/cm ³	1.12
熔体流动速率 Melt-flow rate test	D1238	g/10min	110
熔点 Melting Point	-	℃	-
燃烧性 Flammability	UL-94	1.6mm	V0
热变形 Heatdistortio	D648	0.45Mpa, 6.4mm ℃	190℃
收缩率 Shrinkage ratio	D2732	%	-
硬度 Hardness	D2240	HD	-
灼热丝 GWIT	GB/T5169	℃/mm	-